

PHARMACOPOEIAL DISCUSSION GROUP

REV. 2 CORR. 2

CODE: E-26

NAME: Methylcellulose

(Correction of the sign-off document dated 25 June 2014)

Item to be corrected: Viscosity – sample preparation

“Method 1: Weigh accurately an amount of Methylcellulose, equivalent to 4.000 g, calculated on the dried basis, transfer into a wide mouth bottle, and add hot water (90-99 °C) to obtain the total weight of the sample and water of 200.0 g. ...

Method 2: This method is applied to samples with a viscosity type of 600 mPa · s or higher. Weigh accurately an amount of Methylcellulose, equivalent to 10.00 g, calculated on the dried basis, transfer into a wide mouth bottle, and add hot water (90-99 °C) to obtain the total weight of the sample and water of 500.0 g ...”

European Pharmacopoeia

Signature



Name

W. ESTEL

Date

11/7/15

Japanese Pharmacopoeia

Signature



Name

Haruhiko Okuda
for Kazuhiko Mori

Date

July 1st 2015

United States Pharmacopeia

Signature



Name

KEVIN MOORE

Date

01 - JUL - 2015